

DuploCOLL® 268

Double-sided pressure sensitive adhesive tape coated with a high-performance rubber adhesive

Product construction			
	Name	Colour	Thickness [mm]
Liner	Silicone paper	white	approx. 0,07
Adhesive covered side	Synthetic rubber		
Carrier	Special paper	white	approx. 0,16
Adhesive open side	Synthetic rubber		
Total thickness:			approx. 0,23

Product advantages

- The excellent tack guarantees high initial adhesion. Outstanding adhesion on difficult to bond polymers, like polyethylene, polypropylen and polystyrene
- Good bonding to rubber goods, powder- and standard paints
- The adhesive is water-resistant
- Particularly suitable for smooth and even surfaces

Main application fields

- Mounting of evaporator plates in the refrigerator industry
- Splicing of coated papers, plastic films and metal foils
- Laminating of leather and textiles
- Self-adhesive bonding of rubber goods (mouldings, profiles)
- Bonding to extruded plastic-profiles

Product features

Applicability on

Initial adhesion	● ● ●	Foam	● ● ○
Final adhesion	● ● ●	Rubber	● ● ○
Dimensional stability	● ○ ○	Fabric	● ● ○
Adhesion on even surfaces	● ● ●	Glass/Ceramics	● ● ○
Adhesion on rough surfaces	● ● ○	Wood	● ● ●
Ageing resistance	● ○ ○	High energy plastics: PVC, PC, ABS,...	● ● ●
Weathering resistance	● ● ○	Low energy plastics: PE, PP,...	● ● ●
Chemical resistance	● ○ ○	Metal	● ● ●
Resistance to plasticizers	● ○ ○	Paper/Cardboard	● ● ●

● ● ● very suitable ● ● ○ suitable ● ○ ○ suitable with reductions ○ ○ ○ not suitable

DuploCOLL® 268

Double-sided pressure sensitive adhesive tape coated with a high-performance rubber adhesive

Specific technical data*


Temperature range	-10 °C to +60 °C**
Mounting tape of evaporator plates in refrigerators (experience)	-40 °C, temporary +85 °C
Peel strength to polyethylene after 24 h at room-temperature	25 N/25mm
Peel strength to polypropylene after 24 h at room-temperature	40 N/25mm

* Specific test results, statistically not approved.

** Reached temperature in a rising heat test (SAFT)

Technical Data

Dyn. Shear strength	on stainless steel at +23 °C +/- 2°C	170 N/375 mm ²
Peel strength 180°	on stainless steel at +23 °C +/- 2°C	45 N/25 mm



Application

Recommended application temperature	18 °C to 35 °C
Application guidelines	www.lohmann-tapes.com

Storage

Adhesive tapes should be stored at room temperature and normal humidity (50-70 %).
The storage stability is one year after delivery.

Product presentation

Converted product	Rolls
Width [mm]	1260
Length [m]	2000
Max. log width: 1260 mm	Other dimensions, die-cuts and sheets on request.

For mechanical mounting of this adhesive tape we also offer a wide range of application devices.

DuploCOLL® 268

Double-sided pressure sensitive adhesive tape coated with a high-performance rubber adhesive

IMPORTANT NOTE

The physical characteristics contained in this data sheet represent typical or average values. All application related statements, information and recommendations herein are given to the best of our knowledge and practical experience. Many factors beyond our control and uniquely within buyer's knowledge and control can affect the use and performance of our tape in a particular application. EXCEPT AS EXPRESSIVELY AGREED IN WRITING WE DO NOT TAKE OVER ANY WARRANTY OR LIABILITY FOR THE SUITABILITY OR USABILITY OF OUR TAPES FOR CERTAIN PURPOSES AND APPLICATIONS RESULTING FROM BUYER'S SPECIAL USAGE OF THE TAPES. EXCEPT WHERE PROVIDED BY MANDATORY LEGAL PROVISIONS, WE WILL NOT BE LIABLE FOR ANY DIRECT OR INDIRECT MATERIAL OR IMMATERIAL LOSSES OR DAMAGES ARISING FROM THE USAGE OR APPLICATION OF OUR TAPES. Solely the buyer is responsible for determining the suitability of the specific tape for its use in connection with his method of application. Please consult our Technical Applications Department for specific advice.

Date of issue: December 2023

Lohmann GmbH & Co. KG
Irlicher Strasse 55
56567 Neuwied
Germany
Phone: + 49 (0) 26 31 34 - 0
Fax: + 49 (0) 26 31 34 - 6661
E-mail: info@lohmann-tapes.com

For further information
www.lohmann-tapes.com

